

Artikel	Samenstelling %						Smelttraject		Dichtheid	Treksterkte	Standaard		
	Ag	Cu	Zn	Ni	Mn	Sn	Solidus °C	Liquidus °C			ISO 17672	EN 1044	AWS A5.8
Zonder zink (voor oven solderen)													
Ag60Sn/1	60	30	-	2	-	10	600	730	9,8	-	Ag 160	AG 402	BAG-18
Ag72Cu	72	28	-	-	-	-	780	780	10	35	Ag 272	AG 401	BAG-8
Ag72 V1	72	28	-	-	-	-	780	780	10	35	Ag 272 V1	AG 401 V1	BAG-8 Grade 1
Ag72 V2	72	28	-	-	-	-	780	780	10	35	Ag 272 V2	AG 401 V2	BAG-8 Grade 2